

MOVEMENT OF COINCIDENCE GRAIN BOUNDARIES WITH SIGMA FROM ISOTROPY TO ANISOTROPY

R. Wojnar¹

¹*Institute of Fundamental Technological Research Polish Academy of Sciences, Warszawa, Poland*

e-mail: rwojnar@ippt.pan.pl

1. Isotropy

Isotropy means having the same properties in all directions (1856). The word is derived from the Greek, *isos* (equal) and *tropos* (way). The exact definitions depend on the field in which this concept is used. The opposite of isotropy is anisotropy. The term isotropy is associated with geometry and the concept of direction, while the term of homogeneity is associated with the concept of density. Simple chemical reaction and removal of a substrate by an acid or a solvent or is often close to isotropic. The kinetic theory of gases is also an example of description of the isotropic medium, cf. [1]. In Statistical Physics, for the system of N particles, the two-particle distribution function $n_2 = n_2(\mathbf{r}_1, \mathbf{r}_2)$ is defined as $n_2(\mathbf{r}_1, \mathbf{r}_2) = N(N-1)P_2(\mathbf{r}_1, \mathbf{r}_2)$, where $P_2(\mathbf{r}_1, \mathbf{r}_2)$ is the probability density to find particle nr 1 at \mathbf{r}_1 and nr 2 at \mathbf{r}_2 . For isotropic system $n_2(\mathbf{r}_1, \mathbf{r}_2) = n_2(r_{12})$, cf. [2]. In Chemistry, the electron clouds described by s-orbitals are isotropic, and by other orbitals - anisotropic, cf. [3]. In Economics and Geography, an isotropic region is a region that has the same properties everywhere. The Big Bang theory of the evolution of the observable universe assumes that space is isotropic. It also assumes that space is homogeneous. These two assumptions are known as the Cosmological Principle, [4,5].

Amorphous substances are isotropic, although they do not have to be homogeneous. Polycrystalline bodies may also be isotropic. If the individual crystallites are oriented completely at random, a large enough volume of polycrystalline material will be approximately isotropic. In hydrodynamics, we observe with the increasing velocity the passage from the laminar flow (anisotropic) to turbulent (isotropic) flow, cf. [6].

2. Isotropy and anisotropy in geometry and mechanics

Carl F. Gauss proved that the highest average density in close-packing of equal spheres is equal to $\pi/(3\sqrt{2}) \simeq 0.74048$ in 3D, and $\pi/(2\sqrt{3}) \simeq 0.9069$ in 2D. The Kepler conjecture, recently proved states that this is the highest density that can be achieved by any arrangement of spheres, either regular or irregular, cf. [7-9].

A hexagonal 2D crystal is anisotropic and has three symmetry axes. A deformation in the plane is determined by only two moduli of elasticity, as for an isotropic body, cf. [10]. A symmetric tensor of rank two, such as the thermal conductivity or the thermal expansion tensors have only one component, again as in isotropic medium.

Conversely, an isotropic medium subject to stress acquires anisotropic properties, behaves like a crystal and exhibits the birefringence, [11]. Similarly, the isotropic suspension of magnetic particles (in micrometer or nanometer scale spheres) distributed randomly becomes in the magnetic field an anisotropic solid, [12].

3. Coincidence site lattice

A grain boundary is the interface between two kinds of grains, or crystallites, in a polycrystalline material. The boundary consists of structural units which in the 2-D system depend on the misorientation of the two neighbouring grains. The misorientation angle is given by

$$\alpha = \arccos \frac{d^2 + n^2 - m^2}{2dn} \quad \text{where} \quad d^2 = m^2 + n^2 + mn$$

and m, n are integers. The types of structural unit are described by the concept of the coincidence site lattice (CSL), in which repeated units are formed from points at which the two misoriented lattices happen to coincide.

The degree of fit (Σ) between the lattices of the two grains is described by the reciprocal of the ratio of coincidence sites to the total number of sites

$$\Sigma \equiv \frac{\text{surface of the CSL unit cell}}{\text{surface of the lattice unit cell}}$$

It is possible to draw the lattice for the 2 grains and count the number of atoms that are shared (coincidence sites), and the total number of atoms on the boundary (total number of site). For example, when $\Sigma = 7$ there will be one atom each 7 that will be shared between the two lattices. The misorientation angle $\alpha = 19.1066^\circ$ for $\Sigma = 7$, as in this case $m = 1, n = 2, d = \sqrt{7}$.

4. From isotropy to anisotropy

We are considering a 2-D system of point particles subject to periodic boundary conditions. To ensure uniform homogeneous density of the initial arrangement, we distribute the particles on the honey-comb lattice. In each cell of this lattice we randomly put 7 particles. In such a way the isotropic initial system is created.

Next, all the particles of the system are subjected to the Centroidal Voronoi iterations. One of the 7 particles in each honey-comb cell after a few iterations approaches to the very center of the cell. In this way, a coincidence point appears in the center of each honey-comb cell. After just a few iterations, the system begins to crystallize in two phases of different directions. During the further crystallization convexities and concavities of the grain boundaries are reduced and the grain boundaries straighten.

Thus, the consecutive iterations result in increasing the anisotropy by disappearing some pentagons-heptagons (5-7) pairs. As a result, the percentage of hexagons increases and in consequence the anisotropy is growing. The same procedure could be done for $\Sigma = 13, 19, \dots$ and in general $\Sigma = 6k + 1, k = 4, 5, 6, \dots$. After each iteration we examine the number of hexagons created. The increase in their number is a measure of the departure from isotropy. Finally, we observe the creation of a bicrystal formed by grains of only two kinds. Two phases are separated by the boundary of 5-7-pairs. It is important that contrary to the widespread opinion that the 5-7 pairs are symmetric, these 5-7 pairs do not lie on the boundaries in a symmetrical manner.

If other (not coincident) integer numbers are put in the honey-comb lattice cells, we get polycrystals. But, if $\Sigma = 49 = 7 \times 7$ and $\Sigma = 91 = 7 \times 13$ it is possible to build up interesting tricrystals.

References

- [1] L. D. Landau and E. M. Lifshitz (2011). *Statistical Physics*, Volume 5 (Course of Theoretical Physics), transl. from the Russian J. B. Sykes and M. J. Kearsley, 3rd edit., Butterworth-Heinemann, Oxford OX.
- [2] J. Stecki, *Termodynamika statystyczna*, PWN, Warszawa 1971.
- [3] W. Kołos, *Chemia kwantowa*, PWN, Warszawa 1978.
- [4] C. M. Will (1986) *Was Einstein Right? - Putting General Relativity to the Test*, Basic Books, New York.
- [5] P. J. E. Peebles, D. N. Schramm, E. L. Turner & R. G. Kron (1994). The Evolution of the Universe, *Scientific American* **271** 29–33.
- [6] L. D. Landau and E. M. Lifshitz, *Fluid mechanics*, Volume 6 of Course of Theoretical Physics, transl. from the Russian by J. B. Sykes and W. H. Reid, Second edition, Pergamon Press, Oxford - New York - Beijing 1987.
- [7] T. C. Hales (1998). An overview of the Kepler conjecture, arXiv:math/9811071v2 Mathematics: does the proof stack up?, *Nature* **424**, 12–13.
- [8] H. Cohn, A. Kumar, S. D. Miller, D. Radchenko, M. Viazovska (2017). The sphere packing problem in dimension 24, *Annals of Mathematics* **185** (3) 1017–1033. arXiv:1603.06518
- [9] J. H. Conway, N. J. A. Sloane, E. Bannai (1999). *Sphere packings, lattices, and groups*, Springer Science+Business Media, New York.
- [10] L. D. Landau and E. M. Lifshitz (1970). *Theory of Elasticity*, Volume 7 of Course of Theoretical Physics, transl. from the Russian by J. B. Sykes and W. H. Reid, 3rd edition, Pergamon Press, Oxford - New York - Toronto - Sydney.
- [11] J. F. Nye (1957) *Physical Properties of Crystals: Their Representation by Tensors and Matrices*, Oxford University Press.
- [12] L. J. Frańś, R. B. Pęcherski (2018). Modified split Hopkinson pressure bar for the investigations of dynamic behaviour of magnetorheological materials, *Journal of Theoretical and Applied Mechanics* **56** (1) 323–328.