

8th International PhD Meeting

28. - 29. August 2019

Dresden, Germany

Abstract Booklet



Fraunhofer

IKTS

Controlling of mechanical properties of electrospun PMMA fibers via voltage polarity

Daniel P. Ura^{1*}, Arkadiusz Gradys², Angelika Zaszczynska², Paweł Sajkiewicz², Urszula Stachewicz¹

¹International Centre of Electron Microscopy for Materials Science, Faculty of Metals Engineering and Industrial Computer Science, AGH University of Science and Technology, Poland

²Laboratory of Polymers and Biomaterials, Institute of Fundamental Technological Research, Polish Academy of Sciences, Poland

*e-mail: urad@agh.edu.pl

Abstract

Electrospun polymer fibers due to their surface-to-volume ratio, mechanical properties and porosity are used extensively in various applications like air filtration, triboelectric generators (TEGs) and tissue engineering [1]. Fibers produced by electrospinning have unique mechanical properties due to the manufacturing method [2]. Many process parameters including humidity, flow rate, distance and the applied voltage polarity have significant influence on properties of polymer fibers [3]–[6]. In electrospinning technique, changing a voltage polarity allows to control of surface potential and moving of polymer chains [3], [7]. In our studies, we aim to verify the effect of voltage polarity on structural and surface changes of poly (metacrylate methyl) (PMMA) fiber in terms of their mechanical properties and crystallinity.

In this work, we used PMMA ($M_w=350\,000\text{ g}\cdot\text{mol}^{-1}$) dissolved in dimethylformamide (DMF) to produce aligned and randomly aligned fibers using EC-DIF apparatus. We produce fibers with positive (PMMA+) and negative voltage polarity (PMMA-). Electrospun fibers morphology and diameters were investigated using Scanning electron microscopy (SEM). The mechanical testing of PMMA was performed using a tensile module equipped with a 1N cell. Surface chemistry of the produced electrospun fibers was analyzed with X-ray photoelectron spectroscopy (XPS) with monochromatic radiation from Al K α (1486.6 eV). Crystallinity and glass transition temperature was verified using differential scanning calorimetry (DSC).

The fiber morphology and diameter were similar for both type of random PMMA fibers ($1.51 \pm 0.21\ \mu\text{m}$ for PMMA+ and $1.62 \pm 0.29\ \mu\text{m}$ for PMMA-) and aligned fibers ($1.54 \pm 0.21\ \mu\text{m}$ for PMMA+ and $1.65 \pm 0.31\ \mu\text{m}$ for PMMA-). From the mechanical testing of PMMA+ and PMMA- samples, we obtained the maximum stress for random fibers 129 kPa and 230 kPa, respectively. Interestingly, for aligned fibers we observed opposite effect. For PMMA+ the tensile strength was higher, equal to 320 kPa and PMMA- it was 180 kPa. The variations in mechanical strengths indicated clearly that the highest mechanical stress was obtained for aligned fibers.

Within this study, we showed the potential of controlling mechanical properties of electrospun fibers via voltage polarities. In conclusion, electrospun PMMA fibers were successfully produced using positive and negative voltages with similar average fiber diameters and morphology. Random PMMA fibers produced with positive voltage polarity (PMMA+) proved higher mechanical properties than PMMA fibers produced with negative voltage polarity (PMMA-). For aligned PMMA fibers, we observed reverse effect. The further studies include theoretical analysis of charge effect during electrospinning on their structure in relation to mechanical properties of PMMA fibers.

Acknowledgements

The study was conducted within the funding from SONATA Bis 5 project granted by National Science Centre in Poland, No 2015/18/E/ST5/00230. This research was conducted with infrastructure of International Centre of Electron Microscopy for Materials Science.

References

- [1] J. Ding et al., "Progress in Polymer Science Electrospun polymer biomaterials," vol. 90, pp. 1–34, 2019.
- [2] A. Arinstein, M. Burman, O. Gendelman, and E. Zussman, "Effect of supramolecular structure on polymer nanofibre elasticity," *Nat. Nanotechnol.*, vol. 2, no. 1, pp. 59–62, 2007.
- [3] T. Busolo et al., "Surface potential tailoring of PMMA fibres by electrospinning for enhanced triboelectric performance," *Nano Energy*, vol. 57, no. December 2018, pp. 500–506, 2018.
- [4] P. K. Szewczyk et al., "Roughness and Fiber Fraction Dominated Wetting of Electrospun Fiber-Based Porous Meshes," *Polymers (Basel)*, vol. 11, no. 1, 2019.
- [5] P. K. Szewczyk et al., "Surface-Potential-Controlled Cell Proliferation and Collagen Mineralization on Electrospun Polyvinylidene Fluoride Fiber Scaffolds for Bone Regeneration," *ACS Biom.Sci.Eng.*, 2019.
- [6] P. K. Szewczyk, J. Knapczyk-Korczak, D. P. Ura, S. Metwally, A. Gruszczyoski, and U. Stachewicz, "Biomimicking wetting properties of spider web from *Linothele megatheloides* with electrospun fibers," *Mater. Lett.*, vol. 233, 2018.
- [7] S. Metwall et al., "Single-Step Approach to Tailor Surface Chemistry and Potential on Electrospun PCL Fibers for Tissue Engineering Application," *Adv. Mater. Interfances*, 2018.